

# Depolymerization of Chitosan Using a High Pressure Homogenizer

Jun Hee Cho<sup>a</sup>, Taeyoung Kim<sup>a</sup>, Yun Hye Yeon<sup>a</sup>, Hyun Hyo Kim<sup>a</sup>

<sup>a</sup>Department of Research & Development, ILSHINAUTOCLAVE CO. #835 Taplipdong, Yuseonggu, Daejeon 305-510, Korea

## Application of Chitosan





Problems  
High Viscosity & Large Molecular Weight

## Method of Depolymerization


Process	Method	Advantage	Disadvantage
Physical (Radiation)	Ultrasonic	• No Waste (Acid/Alkali), No-residues	• Long Time Process • Process Noise
	E-beam, $\gamma$ -Ray	• No Waste (Acid/Alkali), No-residues	• Dangerous Process • High Cost
Chemical	Acidic hydrolysis	• High Solubility • High Efficiency of Depolymerization	• Acid waste water • Complex Process
	Phosphorylation Sulfation	• Enhancement of Solubility and Functionality	• Low Efficiency
Biological	Enzymatic hydrolysis	• Selective Decomposition • High Efficiency of Depolymerization	• High Cost • Inefficiency

## 1. Introduction

### High Pressure Homogenizer (HPH, Nano Disperser, ILSHIN AUTOCLAVE)



### High pressure Intensifier



### Fluid Velocity (Sound Speed: 340 m/s)

Pressure (bar)	500	1000	1500	2000	2500
Fluid velocity (m/sec)	313	442	542	626	700

## 2. Experimental

### Experimental


- Natural Polymer: Chitosan
- Solvent: D.I Water
- Nano Disperser: NLM 100

Operating Pressure (bar)	200 – 1500
Max. Flow Rate (ml/min)	100
Pump System	Motor Driven
Dimension (mm)	300*450*300
Weight (kg)	30

### Characterization


- Viscometer
- Gel Chromatograph
- FT-IR
- UV-Vis
- XRD

#### Chitosan structure




Large Molecular Weight  
1 % (w/v) Chitosan Solution

Low Molecular Weight  
1 % (w/v) Chitosan Solution




## 3. Results & Discussion


### Viscosity (1 % (w/v) Chitosan)




### Molecular Weight



### FT-IR Spectrum




### UV-Vis Spectrum



• HPH treatment produces significant changes in the viscosity and molecular weight of the chitosan solution.

• As the pressure and the number of pass increases, the polymer solution shows a significant decrease of viscosity and molecular weight.

### XRD



- The intensity characteristics of the peaks tend to decrease with increasing numbers of passes under high pressure homogenization.
- A decrease in crystallinity occurs due to the destruction of the crystal structure of chitosan as a result of the cleavage of the glycosyl bonds.

- In the HPH process, the pressure and the number of passes increases make viscosity and molecular weight decrease without any acid/alkali solution (Green Chemistry).
- The FT-IR spectra indicated no obvious modification of chemical structure of natural polymer before and after HPH treatment.
- HPH has been shown to be a valid tool to reduce molecular weight of natural polymer (polysaccharides structure).



• High Depolymerization Effect, Short Process Time and No Waste Water (Green Chemistry)

## 4. Conclusion

- In the HPH process, the pressure and the number of passes increases make viscosity and molecular weight decrease without any acid/alkali solution (Green Chemistry).
- The FT-IR spectra indicated no obvious modification of chemical structure of natural polymer before and after HPH treatment.
- HPH has been shown to be a valid tool to reduce molecular weight of natural polymer (polysaccharides structure).

